



The
Patent
Office

10/0039701256

09/673992

INVESTOR IN PEOPLE

**PRIORITY
DOCUMENT**

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

The Patent Office

Concept House

Cardiff Road

Newport

South Wales

NP9 1RH

25 JUN 1999

PCT

A3kU

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.


Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

Signed

Andrew Gersey


Dated

17 May 1999



202279/80

THIS PAGE BLANK (USPTO)



Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

The Patent Office

Cardiff Road
Newport
Gwent NP9 1RH

1. Your reference HL58057/001/WS

2. Patent appli
(The Patent O

9821162.6

29 SEP 1998

3. Full name, address and postcode of the or of each applicant (underline all surnames)

Hugh P Craig
29 Wallace Drive, Eaton Bray, Dunstable, Beds. LU6 2DF

Multicore Solders Limited
Kelsey House, Wood Lane End, Hemel Hempstead,
Hertfordshire, HP2 4RQ

Patents ADP number (*if you know it*)
If the applicant is a corporate body, give the country/state of its incorporation

United Kingdom

4. Title of the invention
Adhesive and Encapsulating Material with Fluxing Properties

5. Full name of your agent (*if you have one*)

Haseltine Lake & Co.

"Address for service" in the United Kingdom to which all correspondence should be sent (*including the postcode*)

Imperial House
15-19 Kingsway
London WC2B 6UD

Patents ADP number (*if you know it*)

34001

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (*if you know it*) the or each application number

Country

Priority application number
(*if you know it*)

Date of filing
(*day/month/year*)

GB

9808587.1

22/04/98

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing
(*day/month/year*)

8. Is a statement of inventorship and of right to a grant of patent required in support of this request? (*Answer "Yes" if:*

No

a) any applicant named in part 3 is not an inventor, or
b) there is an inventor who is not named as an applicant,
or
c) any named applicant is a corporate body.

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

Description 15 13

Claim(s) 6

Abstract 1

Drawing(s) 10

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to a grant of patent (Patents Form 7/77)

Request for preliminary examination and search (Patents Form 9/77)

Request for substantive examination (Patents Form 10/77)

Any other documents (please specify)

11. I/We request the grant of a patent on the basis of this application

Signature

Date

29th September 1998

12. Name and daytime telephone number of person to contact in the United Kingdom

Mr W Silverman

[0171] 420 0500

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered "Yes" Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.

ADHESIVE AND ENCAPSULATING MATERIAL
WITH FLUXING PROPERTIES

5 This invention relates to electrical
interconnection methods in electronic circuitry and
more particularly to flip chip attachment and
encapsulation of both naked semi-conductors and chip
scale packages (CSPs). The technology is commonly
10 referred to as underfill technology.

As is noted in US-A-5 128 746, solder bump
interconnections when attaching chips to electronic
circuitry eliminate the expense, performance
limitations, low productivity and poor space
15 utilisation of wire bonding. As circuit density
increases occur, while circuit board and assembly sizes
continue to shrink, so-called flip-chip interconnection
using solder bumps has proved to be the most suitable
technique for satisfying such demands.

20 With the most common form of flip-chip
interconnection, solder bumps are placed on terminals
of the integrated circuit being produced while the
substrate for the integrated circuit is still in the
form of a small wafer or die. Commonly, the eutectic
25 Sn/Pb 60/40 or a high melting point alloy such as Sn/Pb
3/97, which is known to have been employed in the IBM
C4 process, is employed as solder material. The die or
wafer carrying the integrated circuit is to be joined
to a substrate and for this purpose the die or wafer
30 will be inverted (hence the term flip-chip). It is
current manufacturing practice to place a flux or
solder paste on the substrate. This material will
promote the adhesion of the die to the substrate during
reflow of the solder bump. During reflow, the assembly
35 produced is subjected to a temperature sufficient to
melt or collapse (C4 process) the solder bump and form

the required interconnections. The flux residue must then be removed to prevent corrosion occurring to the die and, importantly, to allow free ingress of a subsequent underfill resin which is to encapsulate the various semi-conductors of the electronic circuitry produced.

For this latter purpose, an underfill encapsulant resin is applied around and under the die following reflow and flux removal. The very small gap between the die and substrate must be completely filled in order to provide environmental protection for the device. The filling of this gap is dependent on capillary action of the encapsulant material between the integrated circuit and substrate. The filling of the gap has proved to be a procedure which is very time consuming, expensive and difficult to achieve in the desired quality and is generally an unreliable procedure, particularly when a relatively large die is used. Moreover, the low viscosity of encapsulant material needed to ensure capillary action runs counter to the need to control thermal expansion and thermal conductivity by filling the encapsulation resin with ceramic powder which generally increases the viscosity of the resin. A solution to this problem has been to heat the substrate/component assembly to reduce initially the viscosity of the underfilling encapsulant resin. Temperatures must be precisely controlled and the process is difficult to control since the elevated temperature triggers the curing mechanism thus raising viscosity prematurely. For these various reasons, the underfilling process currently employed has low productivity and high space/equipment needs.

In the aforementioned US-A-5 128 746, it is proposed to add a fluxing agent to a cross-linking agent - containing encapsulant resin, the encapsulant resin being dispensed onto the substrate before the integrated circuit-carrying chip is placed in the encapsulant resin.

for reflow. US-A-5 128 746 discloses the use of certain strong organic dicarboxylic acids as examples of commercially available fluxing agents. A fluxing encapsulant resin of such type has three very serious drawbacks which compromise the integrity of the interconnection. Free acid remains in the encapsulant after reflow and can and will attack and corrode metal present, especially on the die or wafer. This problem is exacerbated by the decreased environmental resistance of such adhesive composition due to the presence of unreacted resin. As the adhesive composition has relatively low resistance to humidity and moisture, the corrosion problem is thus intensified. Moreover, the addition of acids of the stated type to epoxy resin adhesives compromises the stability of the adhesive, greatly reducing pot life and making cure characteristics variable. This will have a major effect on reliability and process control.

Finally, it is known that salts formed during fluxing of materials by reaction between metal oxides and fluxing agent and containing various metals including tin and lead can have a catalytic action on polymer materials thus causing a premature cure of the polymer prior to reflow of the solder.

It is an object of this invention to provide a thoroughly curable adhesive which does not suffer the problem of unreacted acid remaining in the encapsulant after reflow or the problem of pre-cure of the polymer due to salts formed during fluxing.

According to one aspect of the present invention there is provided a thermally curable adhesive composition which comprises:

- (a) a thermosetting polymer, or a monomer which is polymerisable to yield a thermosetting polymer, said polymer being crosslinkable when subject to the action of a chemical crosslinking agent;

(b) a solid chemical crosslinking agent for said polymer, the crosslinking agent having fluxing properties and being of restricted reactivity with the polymer without the action of a catalyst; and
5 which composition is thermally curable when heated to soldering temperatures in the presence of a catalyst for the crosslinking of the polymer with a crosslinking agent and is storage and reaction stable in the absence of such catalyst and at ambient temperatures.

10 A crosslinking agent to be employed in the practice of the present invention will have fluxing properties so as to enable it to remove oxides from the material with which it is in contact, i.e. die and
15 substrate metallisation and, more particularly, solder metal, thereby allowing solder joint formation. The crosslinking agent, when present in sufficient amount, is to be capable of complete reaction with
thermosetting polymer to neutralise, i.e. react with all reaction sites of the polymer. Excess crosslinking
20 agent has the potential to corrode metal surfaces accessible via pinholes which are often present unavoidably in resin. As a result of excess crosslinking agent remaining trapped in the polymer matrix together with catalyst, this is not a problem.
25 The composition itself is storage and reaction stable until heated to a temperature at which the latent reaction catalyst effectively causes the crosslinking agent to cure the thermosetting polymer and at which temperature the crosslinking agent will have melted and
30 dissolved in the polymer or monomer.

Thus, the present invention provides chip underfill and encapsulation adhesive compositions having fluxing properties which enable one to achieve
35 overall a rugged structure with protection of integrated circuits which have been previously solder bumped and then flip chip connected to a substrate with

a metallisation pattern. During reflow, the fluxing achieved with the crosslinking agent allows metallic interconnection to be achieved between solder bump and metallisation pads on the substrate. The adhesive composition then reacts and cures to provide a fully adhered encapsulate underfill that is non-corrosive and environmentally resistant. The adhesive compositions themselves are stable and provide a long storage life at ambient temperatures, typically 20-25°C, while maintaining predictable processing characteristics. The adhesive compositions lack the substantial debilitating defects in the hitherto known compositions by providing a means for predepositing the underfill and eliminating separate fluxing and cleaning. The adhesive composition may be modified to optimise CTE, glass transition temperature (T_g), elasticity modulus and thermal conductivity without detriment to the aforementioned benefits or detriment to the require rheological properties which allow for ease of deposition, for example by syringe dispensing. In addition, curing is achieved readily during any suitable thermal treatment, for example during reflow soldering. The underfill may only be partially cured after one or several solder reflow cycles, thus enabling ease of reworking of the device. Full cure is then achieved in a separate post-cure heat application. Alternatively, full cure may be obtained from one or two reflow cycles if reworkability is not required.

The invention thus also provides, in a second aspect, a method of producing an electronic device which comprises opposing an electrical component having a plurality of electrical terminations, each termination including a solder bump, and a component-carrying substrate having a plurality of electrical terminations corresponding to the terminations of the electrical component, with a thermally curable adhesive

composition according to the first aspect of the invention being applied to a metal surface at one and/or both of said electrical component and said substrate, bringing the electrical component and substrate into contact at elevated temperature and thereby soldering the electrical component to the substrate and simultaneously achieving encapsulation thereof in thermoset polymer produced from said monomer or polymer in situ, catalysis of crosslinking of the thermally curable adhesive being achieved by metal oxide removed from metal surfaces by the fluxing composition and/or salts formed by reaction between metal oxide and crosslinking agent.

Insofar as the solder is concerned, this may consist of one or more metals which provide a suitable low melting point material. The metals employed are typically selected from tin, lead, bismuth, cadmium, zinc, gallium, indium, tellurium, mercury, thallium, antimony and selenium. The preferred such metal is tin or a tin/lead alloy. Specific examples of solders which may be employed are the aforementioned eutectic Sn/Pb 60/40 and the high melting point Sn/Pb 3/97.

The thermosetting polymer or monomer utilised in the compositions of this invention is an adhesive substance which is preferably liquid at ambient temperature. Thus one may utilise a reactive polyester or an epoxide monomer or polymer such as an epoxy Novolak or epoxide precursor thereof. A preferred epoxy resin is either a diglycidyl ether of bisphenol A or a diglycidyl ether of bisphenol F. In preferred practice, such an epoxy resin is a B-stage resin or a resin which may be "B-staged" after application, thereby making it possible for there to be a delay before bringing together the component and the substrate. Other preferred epoxy materials to use are substances from the Araldite series of Ciba-Geigy

Resins, such as the trifunctional epoxide MY10510 and the difunctional cycloaliphatic epoxide ERL 4221 which may be used singly or in admixture. The Araldite MY10510 may be replaced by Aradite MY9512, a tetra-
5 functional epoxide. MY9512 may be used alone, too, as may the trifunctional epoxide MY10510. The composition of the invention may also contain a monomer precursor for a polymer, e.g. an epoxide compound when an epoxy resin is required. Mixtures of such epoxy materials
10 may also be used.

The crosslinking agent with fluxing properties is preferably a di- or polycarboxyl compound which is solid at ambient temperature and insoluble in the monomer or polymer until heated, in practice generally to
15 soldering temperatures, and such cross linking agents are generally referred to hereafter as polyacids. Such polyacids serve as a fluxing agent for the oxide material present on the solder, which metal oxide is a catalyst for reaction between an epoxy resin and the
20 carboxyl groups of the polymer at elevated temperatures. Such polyacid may be in particular a carboxylated polymer, a polymer fatty acid, such as a dimerised or trimerised fatty acid, or a long chain (C_8 or greater, preferably C_{10} or greater) polycarboxylic acid, preferably dicarboxylic acid. An organic trimer
25 fatty acid having a functionality greater than 1 provides more than one reaction site, with an epoxy resin then serving to create a macromolecule that provides adhesive. The aforementioned preferred
30 carboxyl-containing polymers also provide multiple reaction sites. A particularly preferred example of a polymer containing two or more carboxyl groups which may be employed is a styrene-acrylic acid copolymer. A preferred dicarboxylic acid is dodecanedioic acid
35 (DDDA).

Other crosslinking agents with fluxing properties

which can be used are mono di-and polyhydrazides which are solid at ambient temperature and insoluble in the monomer or polymer until heated, in practice generally to soldering temperature. A preferred such compound is adipic dihydrazide. Because of the differing reactivities of polycarboxylic acids and hydrazides, it is preferred to use a mixture of crosslinking agents, such as dodecanedioic acid and adipic dihydrazide, the higher reactivity of the latter being countered by the lower reactivity of the former.

While the oxide removed from the solder or a salt produced by reaction between the polyacid and such oxide, as a result of the fluxing activity of the crosslinking agent, acts as a catalyst for the curing of the polymer, curing in the manner of a snap cure fix is achieved only when an imidazole is present as catalyst active at the elevated temperature utilised for soldering. A preferred such compound is phenyl imidazole. This effect is often not desirable as it is contrary to the need to adjust positioning of components during soldering. Other latent reaction catalysts which can be used are tertiary amines with the amine groups optionally substituting the reactive monomer or polymer, as in the aforesaid Araldite MY10510 or MY9512, or metallic salts such as tin octanoate, dibutyl tin dilaurate, ferric acetylacetonate, and cobalt (III) acetylacetonate.

Preferred compositions embodying the invention will have a thermosetting polymer-crosslinking agent/flux content in which there are from 45 to 70%, more preferably 50 to 60%, by weight of thermosetting polymer and from 30 to 55% by weight, more preferably 40 to 50%, by weight crosslinking agent/flux.

The use in adhesive compositions employed for encapsulating flip chip connections of ceramic powders to enhance thermal expansion and modulus properties of

the composition has already been mentioned herein and is preferably to be adopted in the practice of the present invention. It is preferred that such ceramic powders be highly thermally conductive to enhance the connection between solder bump and conductor on the substrate while ensuring that the compositions retain the low viscosity necessary for fluxing and for ease of deposition. The filler is preferably a nominally 25μ diameter spherical ceramic bead or hollow sphere composition. More generally, it maybe a glass or ceramic powder comprising spherical particles of $5-75\mu$ diameter or comprise essentially monodisperse spherical particles having a single diameter of $5-75\mu$. The ceramic powder has preferably a very high thermal conductivity. Examples of such ceramic powders which may be employed are SiO_2 , MgO , Al_2O_3 , TiO_2/ZnO , barium sulphate and diamond dust. In some cases, it is preferred that the ceramic powder utilised has instead a very low or negative coefficient of thermal expansion, too, and if this requirement is imposed on the ceramic powder then a preferred example is aluminium lithium silicate.

Metal oxides formed on solder metals even at ambient temperatures are themselves a problem since they can catalyse crosslinking of the thermosetting resin or its monomer precursor. In accordance with a preferred embodiment of the invention, the resin or precursor contains an acid flux which is liquid at temperatures below 100°C , preferably below 40°C , more preferably ambient temperature. This acid will react with oxides to form salts which will not decompose until at elevated temperatures, in particular soldering temperatures when the resulting oxides, together with oxides formed on the metal surfaces more readily at the higher temperatures and removed from the metal surfaces by the flux/crosslinking agent, will catalyse the

crosslinking of the thermosetting polymer.

The term "acid" as such is used herein to denote the more volatile flux for preventing prepolymerisation/crosslinking and to distinguish it from the solid crosslinking agent/flux. The more volatile flux is generally liquid at ambient temperature so that it acts immediately as a flux. It should certainly be liquid, at least at temperatures below those at which the crosslinking agents used become fully reactive in the presence of metal oxide/salt crosslinking catalysts. It is thus preferred that the acid used for preventing prepolymerisation, even if solid at ambient temperature, is liquid by 40°C.

Such liquid acids may be polyacids, but will normally be monocarboxylic acids. The acids preferably contain at least 8 carbon atoms and are exemplified by versatic acids, in particular versatic 10 which is a synthetic acid composed of a mixture of highly branched isomers of C₁₀ monocarboxylic acids, mainly of tertiary structure. The high degree of branching gives rise to steric hindrance which means that the salts formed are thoroughly stable and difficult to break down. Other acids which may be used are capric acid, caprylic lauric acid, stearic acid and palmitic acid.

When such monocarboxylic acids are to be used, compositions embodying the invention preferably will have a thermosetting polymer - flux content in which there are 45 to 70%, more preferably 50 to 60%, by weight of thermosetting polymer and from 30 to 45%, more preferably 40 to 50%, by weight of a mixture of fluxes, the flux components consisting of from 80 to 97%, preferably 85 to 95%, by weight of solid crosslinking agent/flux and from 3 to 20%, preferably 5 to 15%, by weight of acid flux which is liquid at below 100°C.

When utilising the compositions of the invention, there is no need for them to be introduced subsequent to formation of a solder connection with the attendant difficulties identified above. It is possible for the composition to be predeposited, before emplacement and soldering of electronic component to substrate, on either or both of the electronic component and the substrate. As there is no need for a separate fluxing agent to be employed which is not incorporated in the adhesive composition, the presence of the composition on one or other of the electronic component and the substrate fulfils the required fluxing function. Insofar as the composition may be applied to the electronic component, then this may be to the die overall whether it is in wafer form or as separate discrete devices. Application of the composition may be by screen printing, stencil printing, dispensing, spinning or any other known method for applying a composition to discrete areas.

The ease of working in accordance with the method of this invention enables the composition to contain the thermosetting resin in the form of a B-stageable precursor for application to die, substrate or carrier tape and then B-staging so as to form a handleable film which becomes fully crosslinked only when the soldering operation is carried out.

The following examples illustrate the adhesive compositions which may be used in the practice of this invention. In the examples all percentages are percentages by weight.

Example 1

ERL 4221	40.6%
MY9512	12.7%
DDDA	46.7%

This composition was functionally good and of satisfactory viscosity for most applications.

Example 2

ERL 4221	39.65%
Epoxy MY9512	12.40%
DDDA	41.05%
Versatic 10	6.90%

This composition was functionally good in not undergoing pre-crosslinking but had too low a viscosity for some applications. As a result, higher viscosity compositions as follows were made up and found to work well.

Example 3

ERL 4221	33.45%
MY9512	18.60%
DDDA	41.05%
Versatic 10	6.90%

Example 4

ERL 4221	26.05%
MY9512	26.00%
DDDA	41.05%
Versatic 10	6.90%

Example 5

ERL 4221	12.40%
MY9512	39.65%
DDDA	41.05%
Versatic 10	6.90%

The initial viscosity of the composition is here somewhat too high for ease of use. Moreover, while Examples 2 to 5 made use of monocarboxylic acids liquid at ambient temperature, it is also possible to use monocarboxylic acids solid at ambient temperature but liquid at temperatures below those at which the crosslinking agent/flux are, for example, as follows:-

Example 6

	ERL 4221	39.65%	
	Epoxy MY9512	12.40%	
	DDDA	41.05%	
5	Prifrac2960	6.90%	(C16 Palmitic acid - solid metals at 60°C)

Example 7

	ERL 4221	39.65%	
10	Epoxy MY9512	12.40%	
	DDDA	41.05%	
	Versatic 10	6.90%	(C18 - melts at 69°C)

15 Finally compositions were formulated which
contained lower amounts of monocarboxylic acid. These,
too, proved to be satisfactory.

Example 8

	ERL 4221	39.65%	
20	MY9512	12.40%	
	DDDA	44.95%	
	Versatic 10	3.00%	

Example 9

25	ERL 4221	42.62%	
	MY9512	13.33%	
	DDDA	41.05%	
	Versatic 10	3.00%	

CLAIMS

1. A thermally curable adhesive composition which comprises:

5 (a) a thermosetting polymer, or a monomer which is polymerisable to yield a thermosetting polymer, said polymer being crosslinkable when subject to the action of a chemical crosslinking agent;

10 (b) a solid chemical crosslinking agent for said polymer, the crosslinking agent having fluxing properties and being of restricted reactivity with the polymer without the action of a catalyst; and which composition is thermally curable when heated to soldering temperatures in the presence of a catalyst for the crosslinking of the polymer with a crosslinking
15 agent and is storage and reaction stable in the absence of such catalyst and at ambient temperatures.

2. A composition according to claim 1, wherein said chemical crosslinking agent is selected from polyacids
20 and hydrazides which are solid at ambient temperature and insoluble in the monomer or polymer until heated to soldering temperature.

3. A composition according to claim 2, wherein the
25 polyacid is selected from dimerised and trimerised fatty acids, polymers containing two or more carboxyl groups and di- and polycarboxylic acids.

4. A composition according to claim 3, wherein the
30 polycarboxylic acid is a C₈ or greater dicarboxylic acid.

5. A composition according to claim 2, wherein the
35 hydrazide is a monohydrazide, dihydrazide or polyfunctional hydrazide.

6. A composition according to any one of claims 2 to 5, wherein the crosslinking agent contains a dihydrazide and/or a dicarboxylic acid.

5 7. A composition according to claim 6, wherein the crosslinking agent contains adipic dihydrazide and/or dodecanedioic acid.

10 8. A composition according to claim 3, wherein the crosslinking agent is a styrene acrylic acid copolymer.

15 9. A composition as claimed in any preceding claim which contains from 45 to 70 parts by weight of thermosetting resin.

10. A composition according to any one of claims 1-8, wherein said polymer is an epoxy resin.

20 11. A composition according to claim 10, wherein said polymer is a B-staged epoxy resin.

12. A composition according to claim 11, wherein the said polymer is a diglycidyl ether of bisphenol A.

25 13. A composition according to claim 9, wherein the said resin is a tri- or tetrafunctional epoxide or a difunctional cycloaliphatic epoxide or a mixture of two or more such epoxides.

30 14. A composition according to any preceding claim, which has a thermosetting polymer - solid crosslinking agent/flux content in which there are from 45 to 70% by weight of thermosetting polymer and from 30 to 55% by weight of solid crosslinking agent/flux.

35

15. A composition according to Claim 14, wherein said

thermosetting polymer content is from 50 to 60% by weight and said solid crosslinking agent/flux content is from 40 to 50% by weight of the total amount of thermosetting polymer and crosslinking agent/flux.

5

16. A composition according to any preceding claim, which additionally contains an acid flux which is liquid at temperatures below 100°C.

10

17. A composition according to Claim 16, wherein the acid flux is liquid at ambient temperature.

15

18. A composition according to Claim 16 or 17, wherein the acid flux is a monocarboxylic acid, preferably containing at least 8 carbon atoms.

20

19. A composition according to Claim 18, wherein the acid flux is a versatic acid, capric acid, caprylic acid, lauric acid, stearic acid or palmitic acid.

25

20. A composition according to any one of Claims 16 to 19, which has a thermosetting polymer-flux content in which there are from 45 to 70% by weight of thermosetting polymer and from 30 to 55% by weight of flux, which flux is, in turn, made up from 80 to 97% by weight of said solid crosslinking agent/acid flux and from 3 to 20% by weight of said acid flux.

30

21. A composition according to Claim 20, which has a thermosetting polymer-flux content in which there are from 50 to 60% by weight of thermosetting polymer and from 40 to 50% by weight of flux, which flux is, in turn, made up from 85 to 95% by weight of said solid crosslinking agent/flux and from 5 to 15% by weight of said acid flux.

35

22. A composition according to any preceding claim, which additionally contains a latent reaction catalyst selected from tertiary amines and imidazoles and metallic salts.

5

23. A composition according to Claim 22, wherein the imidazole is phenyl imidazole.

10

24. A composition according to Claim 22, wherein the tertiary amine is constituted by self catalysing tertiary amine groups substituting the reactive monomer or polymer.

15

25. A composition according to Claim 24, wherein the reactive monomer is a tertiary amine-substituted trifunctional or tetrafunctional epoxide.

20

26. A composition according to Claim 22, wherein the metallic salt is tin octanoate, dibutyl tin dilaurate, ferric acetylacetonate, and cobalt (III) acetylacetonate.

25

27. A composition according to any preceding claim which further comprises a thermally resistant filler.

30

28. A composition according to Claim 27, wherein said filler reduces thermal expansion of the composition while not effecting substantially the viscosity thereof.

35

29. A composition according to Claims 27 and 28, wherein the filler is constituted by nominally 25μ spherical ceramic beads or hollow spheres.

30. A composition according to Claim 27, wherein the filler is a ceramic or glass ceramic powder comprising

spherical particles with diameters in the range from 5-75 μ .

5 31. A composition according to Claim 27, wherein the filler is a ceramic or glass ceramic powder consisting essentially of monodisperse spherical particles having a single diameter in the range from 5-75 μ .

10 32. A composition according to Claim 27, wherein the filler is a thermally conductive ceramic powder.

15 33. A composition according to Claim 32, wherein the ceramic powder is selected from SiO₂, MgO, Al₂O₃, TiO₂/ZnO, barium sulphate and diamond dust.

34. A composition according to Claim 27, wherein the ceramic powder has a low or negative coefficient of thermal expansion.

20 35. A composition according to Claim 34, wherein the ceramic material is aluminium lithium silicate.

25 36. A method of producing an electronic device which comprises opposing an electrical component having a plurality of electrical terminations, each termination including a solder bump, and a component-carrying substrate having a plurality of electrical terminations corresponding to the terminations of the electrical component, with a thermally curable adhesive
30 composition according to any one of claims 1 to 35 being applied to a metal surface at one and/or both of said electrical component and said substrate, bringing the electrical component and substrate into contact at elevated temperature and thereby soldering the
35 electrical component to the substrate and simultaneously achieving encapsulation thereof in

thermoset polymer produced from said monomer or polymer in situ, catalysis of crosslinking of the thermally curable adhesive being achieved by metal oxide removed from metal surfaces by the fluxing composition and/or salts formed by reaction between metal oxide and crosslinking agent.

37. A method as claimed in Claim 36, wherein the thermally curable adhesive composition is applied to one and/or both of the said electrical component and said substrate prior to bringing the two together.

38. A method as claimed in Claim 36 or 37, wherein no fluxing agent is applied to either said electrical component or said substrate prior to application of the solder curable adhesive composition.

39. A method as claimed in any one of Claims 36 to 38, wherein the thermally curable adhesive composition is applied to a die, which is either in wafer form or as separate discrete devices.

40. A method as claimed in any one of Claims 36 to 39, wherein the thermally curable adhesive composition is applied by screen printing, stencil printing, dispensing or spinning.

41. A method as claimed in any one of Claims 36 to 40, wherein the thermally curable adhesive composition is applied in B-stageable form and B-staged in situ.

ABSTRACT

ADHESIVE AND ENCAPSULATING MATERIAL
WITH FLUXING PROPERTIES

5

10

15

Use is made in attachment of an electrical component to an electrical termination on a component-carrying substrate by a solder bump technique of a thermally curable adhesive composition for encapsulating purposes which comprises a thermosetting polymer and a solid chemical crosslinking agent which has fluxing properties but which is of restricted reactivity with the polymer without the action of catalyst. The composition is to be thermally curable when heated to soldering temperatures in a reaction which is catalysable merely by metal oxide fluxed from metal surfaces by crosslinking agent then dissolved in the thermosetting polymer.

THIS PAGE BLANK (USPTO)

PCT/GB99/01236

Haseltine Lake & Co

22/4/99

9821162.6

THIS PAGE BLANK (USPTO)